



Issued on October 25, 2024

PRODUCTION CODE: TBD

GENERAL DESCRIPTION:

Polyethylene film for construction usage,

PRODUCT DESCRIPTION:

Rolls Clear, Super-Six™ Material

Storage Conditions	25°C, 80% RH maximum		
The item is recyclable with Resin Identification Code 4, LDPE.			
	ASTM	Units	Typical Values
Ultimate Tensile Strength in MD	D 882	MPa	>12
Ultimate Tensile Strength in TD	D 882	MPa	>10
Elongation at break in MD	D 882	%	>225
Elongation at break in TD	D 882	%	>350
Impact strength	D1709 Method B	g	300
Thickness – Average	D6988 Method A	µm	150

Disclaimer:

This information represents our best judgment based on work done in our lab, but the company assumes no liability whatsoever in connection with the use of information or findings contained herein. Customers need to confirm the performance in their own specific application environment to validate fit for use".

QUALITY MANAGEMENT SYSTEM
ISO 9001
REGISTERED

GLOBAL FOOD SAFETY INITIATIVE (GFSI)
FOOD SAFETY SYSTEM FSSC 22000
REGISTERED